

Amendments to the Specification

Please replace paragraph [0032] of the published application with the following amended paragraph:

[0032] As a photo-polymerization initiator (C) contained in the composition according to the present invention, 1-hydroxycyclohexyl phenyl ketone, ~~2,2-dimethoxy-2-phenylacetophenodroxy-2-methyl-1-phenylpropane-1-one~~ 2,2-dimethoxy-2-phenylacetophenone, 2-hydroxy-2-methyl-1-phenylpropane-1-one, 1-[4-(2-hydroxyethoxy)-phenyl]-2-hydroxy-2-methyl-1-propane-1-one or 2-methyl-[4-(methylthio)phenyl]-2-morpholino-1-propane is preferable, and it can be used in an optional proportion of alone or a mixture of at least two sorts thereof. A content of the photo-polymerization initiator (C) is usually 0.5 to 20%, preferably 1 to 10%, based on the total weight of the composition according to the present invention.